

S 560

Gümüş Alaşımli Kadmiyum İçermeyen Sert Lehim Telleri

Mekanik ve fiziksel özellikler

Erime Aralığı	C°	620/655
Çalışma Sıcaklığı	C°	655
Gerilme direnci	Mpa	350
Elektriksel iletkenlik	% IACS	11,9
Yoğunluk	gr/cm ³	9,49
Uzama Katsayısı	%	25

Spesifikasyonlar

EN ISO 17672	Ag 156
DIN 8513	L-Ag56Sn
AWS A5.8	B-Ag7
DIN EN 1044	AG 102
EN ISO 3677	B-Ag56CuZnSn-620/655

Ana elementler %(min-max)

Ag : 55-57 / Cu : 21-23 / Zn : 15-19 / Sn : 4,5-5,5

Diğer %

Impurity : 0,15 max

Uzama Katsayısı %

25

RoHS Limit ppm

Cd (100ppm) ; Pb / Hg / Cr (1000ppm)

Availability

Çubuk Tel

Kaplanmış Tel

Kangal / Tel

Yassı Levha

Preform

Toz

Macun

FW



Liability - Disclaimer: This document is intended to assist the user in choosing the product. We provide these results in all conscience; this not however exempting the consumer from the obligation to check our products and process on his own responsibility, including suitability, compliance with applicable law and non-infringement of the rights of others. The company ASA KAYNAK cannot be held liable in respect thereof.

ASA KAYNAK ve METAL ALAŞIMLARI SAN. ve TİC. A.Ş.

Veliköy OSB Sanayi Mahallesi 22. Cad. 4/A
Veliköy / Çerkezköy / Tekirdağ / Turkey 59500
Phone: +90 282 746 1004

www.asakaynak.cominfo@asakaynak.com