

T 440

Gümüş Alaşımli Kadmiyum İçermeyen Sert Lehim Telleri

Mekanik ve fiziksel özellikler

Erime Aralığı	C°	675/735
Çalışma Sıcaklığı	C°	735
Gerilme direnci	Mpa	400
Elektriksel iletkenlik	% IACS	19
Yoğunluk	gr/cm ³	8,9
Uzama Katsayısı	%	25

Spesifikasyonlar

EN ISO 17672		Ag 244
DIN 8513		-
AWS A5.8		-
DIN EN 1044		AG 203
EN ISO 3677		B-Ag44CuZn-675/735

Ana elementler %(min-max)

Ag : 43-45 / Cu : 29-31 / Zn : 24-28

Diğer %

Impurity : 0,15 max

Uzama Katsayısı %

25

RoHS Limit ppm

Cd (100ppm) ; Pb / Hg / Cr (1000ppm)

Availability

Çubuk Tel	Kaplanmış Tel	Kangal / Tel	Yassı Levha	Preform	Toz	Macun	FW
●	●	●	●	●	○	○	●

Liability - Disclaimer: This document is intended to assist the user in choosing the product. We provide these results in all conscience; this not however exempting the consumer from the obligation to check our products and process on his own responsibility, including suitability, compliance with applicable law and non-infringement of the rights of others. The company ASA KAYNAK cannot be held liable in respect thereof.

ASA KAYNAK ve METAL ALAŞIMLARI SAN. ve TİC. A.Ş.

Veliköy OSB Sanayi Mahallesi 22. Cad. 4/A
Veliköy / Çerkezköy / Tekirdağ / Turkey 59500
Phone: +90 282 746 1004

www.asakaynak.cominfo@asakaynak.com