

T 502

Gümüş Alaşımli Kadmiyum İçermeyen Sert Lehim Telleri

Mekanik ve fiziksel özellikler

Erime Aralığı	C°	660/705
Çalışma Sıcaklığı	C°	705
Gerilme direnci	Mpa	-
Elektriksel iletkenlik	% IACS	15
Yoğunluk	gr/cm ³	8,98
Uzama Katsayısı	%	-

Ana elementler %(min-max)

Ag : 49-51 / Cu : 19-21 / Zn : 26-30 / Ni : 1,5-2,5

Uzama Katsayısı %

-

RoHS Limit ppm

Cd (100ppm) ; Pb / Hg / Cr (1000ppm)

Spesifikasyonlar

EN ISO 17672		Ag 450
DIN 8513		-
AWS A5.8		B-Ag24
DIN EN 1044		-
EN ISO 3677		B-Ag50CuZnNi-660/705

Diğer %

Impurity : 0,15 max

Availability

Çubuk Tel	Kaplanmış Tel	Kangal / Tel	Yassı Levha	Preform	Toz	Macun	FW
●	●	●	○	○	○	○	●

Liability - Disclaimer: This document is intended to assist the user in choosing the product. We provide these results in all conscience; this not however exempting the consumer from the obligation to check our products and process on his own responsibility, including suitability, compliance with applicable law and non-infringement of the rights of others. The company ASA KAYNAK cannot be held liable in respect thereof.

ASA KAYNAK ve METAL ALAŞIMLARI SAN. ve TİC. A.Ş.

Veliköy OSB Sanayi Mahallesi 22. Cad. 4/A
Veliköy / Çerkezköy / Tekirdağ / Turkey 59500
Phone: +90 282 746 1004

www.asakaynak.cominfo@asakaynak.com