# CUP 606
## Bakır-Fosfor Alaşımlı Sert Lehim Telleri

### Mekanik ve fiziksel özellikler

| | | |
|---|---|---|
| Erime Aralığı | C° | 710-825 |
| Çalışma Sıcaklığı | C° | 730 |
| Gerilme direnci | Mpa | |
| Elektiriksel iletkenlik | % IACS | |
| Yoğunluk | gr/cm³ | |
| Uzama Katsayısı | % | |

### Spesifikasyonlar

| | | |
|---|---|---|
| EN ISO 17672 | | CuP 180 |
| DIN 8513 | | L-CuP7 |
| AWS A5.8 | | |
| DIN EN 1044 | | CP 202 |
| EN ISO 3677 | | B-Cu93P-710/825 |

### Ana elementler %(min-max)

P: 6,4-6,8 / Cu: Bal.

### Diğer %

Impurity : 0,25 max

**RoHS Limit ppm**
Cd (100ppm) ; Pb / Hg / Cr (1000ppm)

### Availability

| Çubuk Tel | Kaplanmış Tel | Kangal / Tel | Yassı Levha | Preform | Toz | Macun | FW |
|---|---|---|---|---|---|---|---|
| ● | ○ | ● | ○ | ○ | ○ | ○ | ● |

Liability - Disclaimer: This document is intended to assist the user in choosing the product. We provide these results in all conscience; this not however exempting the consumer from the obligation to check our products and process on his own responsibility, including suitability, compliance with applicable law and non-infringement of the rights of others. The company ASA KAYNAK cannot be held liable in respect thereof.

**ASA KAYNAK ve METAL ALAŞIMLARI SAN. ve TİC. A.Ş.**
Veliköy OSB Sanayi Mahallesi 22. Cad. 4/A
Veliköy / Çerkezköy / Tekirdağ / Turkey 59500
Phone: +90 282 746 1004
www.asakaynak.com
info@asakaynak.com